

Amendments to the Specification

Please replace the paragraph beginning on page 9, line 6, with the following rewritten paragraph:

According to a preferred embodiment of the invention, the anti-fouling paint has a binder comprising a blend of a rosin material and an auxiliary film-forming resin in a weight ratio of 20:80 to 95:5, the auxiliary film-forming resin comprising 20-100% by weight of the total weight of the auxiliary film-forming resin of a quaternary ammonium- and/or quaternary phosphonium-functional film-forming polymer (A), the quaternised groups of which are blocked by groups capable of hydrolyzing, dissociating or exchanging with seawater species to leave a polymer soluble in seawater, the blocking groups being anionic residues of acids having an aliphatic, aromatic, or alkaryl hydrocarbon group comprising 6 or more carbon atoms, and ~~80-20%~~80-0% by weight of the total weight of the auxiliary film-forming resin of a non-hydrolysing, water-insoluble film-forming polymer (B).